

Capalac LackSpachtel

Patch-filler and surfacer for exterior and interior use



Product Description

Field of Application	Synthetic resin filling compound for surfacing of wood, primed metals and non-alkaline renders/plasters.
Product Properties	<ul style="list-style-type: none"> ■ Quick-drying. ■ High filling properties. ■ Minor shrinking. ■ Directly overcoatable.
Product Base / Vehicle	Synthetic resin combination.
Packaging/Package Size	250 g tube; 800 g can
Colours	White
Storage	Keep in a cool, but frost-free place.
Technical Data	<ul style="list-style-type: none"> ■ Density: approx. 1.9 g/cm³

Application

Suitable Substrates	<p>Primed wood, metals and existing non-alkaline renders / plasters with sufficient strength. On wooden surfaces in the exteriors do only smoothen to achieve pore-filling or apply for repairs of small defects. In Germany: Smoothening of plain surfaces made of wooden components outdoors is not permitted: See BFS Data Sheet No. 18.</p> <p>Smoothen only on small scale spots of metal surfaces - outdoors. Apply only on interior plaster/render surfaces.</p>
Substrate Preparation	The substrate must be sound, dry and clean.



Substrate	Priming Coat
Untreated wood	Capalac Vorlack Capalac Holz-Imprägniergrund (only for exteriors)
Sound/Solid existing enamel coatings	Capalac Vorlack or Disbon 481 EP-Uniprimer
Iron, steel	Capalac Rostschutzgrund or Capalac AllGrund
non-alkaline renders / plasters	Caparol OptiGrund E.L.F.

Method of Application

Capalac Lackspachtel can be applied repeatedly, wet-on-wet in multiple layers per day, by using a suitable filling/surfacing tool. The maximum wet-layer thickness per working day should not exceed 700 µm. In case of patch-filling, undercoat-varnishing is necessary before the final coating.

Surface Coating System

Capalac Lackspachtel can be coated with synthetic resin and dispersion enamels of the Caparol Group of Companies.

Application Conditions

Working Temperatures:

Min. 15° C and max. 30° C, for product, substrate and ambient air.

Drying/Drying Time

At 20° C and 60 % relative humidity recoatable after over-night drying (wet-layer thickness of max. 700 µm per working-day).

Advice

Special Risks (Hazard Note) / Safety Advice (Status as at Date of Publication)

Keep out of the reach of children. Keep away from sources of ignition — No smoking. Avoid contact with skin and eyes. Do not empty into drains, water courses and onto the ground. Use only in well-ventilated areas. Contains Cobaltcarboxylate, 2-Butanonoxim - can cause allergic reactions. Further Details: See Safety Data Sheet (MSDS).

Disposal

Materials and all related packaging must be disposed of in a safe way in accordance with the full requirements of the local authorities. Particular attention should be made to removing wastage from site in compliance with standard construction site procedures. In Germany: Only completely emptied containers should be given for recycling. Hence, dispose containers with residues at a special waste collection centre accepting used varnish

EU limit value for the VOC content

This product is not subject to the VOC limit values.

Product Code Paints and Enamels

M-GP02

Customer Service Centre

Tel.: (+49) 0 61 54 / 71 17 10
Fax: (+49) 0 61 54 / 71 17 11
e-mail: kundenservicecenter@caparol.de

International Distribution: Please see www.caparol.com

Technical Information No. 094 · Issue: August 2011

All suggestions and application instructions herein are based on our latest technical experience. Due to the wide variety of individual project conditions, we cannot be held responsible for their content. These instructions do not release the purchaser/ applicator from his responsibility to determine the suitability of the product in consideration of the project characteristics. These instructions are to be considered void when a new edition is released. Our general conditions of sale and delivery in their latest edition apply. This document is a translation of our German Technical Information No. 094 · Capalac LackSpachtel · Issued: January 2010

DAW International Business: **Deutsche Amphibolin-Werke von Robert Murjahn Stiftung & Co KG** · P.O.B. 1264 · D-64369 Ober-Ramstadt · Tel. +49 6154 71-1274
Fax +49 6154 71-1264 · E-mail export@daw.de · Internet www.caparol.com